



Take this report to your local sand quarry and have them reference the chart based on your arena being Indoor or Outdoor. They should be able to provide you a sand that is formulated to the sand analysis.

TYPE: Outdoor Sand Sieve

**OUTDOOR**

US Mesh	Grams Retained	% Retained Cumulative	% Passing	Target	% Retained Per Sieve
18	0.1	0.10	99.90	0.00	0.10
35	9.2	9.34	90.66	7.40	9.24
60	61.0	61.93	38.07	48.50	52.59
100	92.8	94.21	5.79	34.00	32.28
140	97.7	99.19	0.81	7.40	4.97
270	98.3	99.80	0.20	1.50	0.61
PAN	98.5	100.00	0.00	0.00	0.20

Type: Indoor Sand Sieve

**INDOOR**

US Mesh	Grams Retained	% Retained Cumulative	% Passing	Target	% Retained Per Sieve
18	0.0	0.00	100.00	0.00	0.00
35	6.0	6.13	93.87	7.40	6.13
60	44.2	48.20	51.80	48.50	42.07
100	81.4	80.10	19.90	34.00	31.90
140	87.3	89.50	10.50	7.40	9.40
270	88.1	90.72	9.28	1.50	1.22
PAN	88.1	90.72	9.28	0.00	0.00